



EPOAIS 10, BI-COMPONENT ADHESIVE BASED ON EPOXY RESINS



Description

High performance adhesive, two-component epoxy resins. Epoais 10 is ideal for bonding fresh concrete with curing concrete. Supports incorporating ARCUAIS.

Application

Epoais 10 is used in binding building materials, its most specific application is as a bonding bridge between new concretes and existing concretes.

Surface preparation

Must be well cleaned, free of greases, oils, stagnant water or loose parts, using sandblasting, abrasive blasting, milling, compressed air or wire brush, for cleaning according to the degree of contamination of the holder.

Modes of application

Stir the content of each package so as to obtain a uniform blend.

- Mix together by adding component B to component A. When not using the whole amount, the required proportions should be used as indicated.

- Mix manually or using a low speed electric mixer (400-500 rpm).

Mix in a proportion of 53A : 47B in weight



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email: desarrollo@teais.es

síguenos en:



- Once mixed, use immediately within an open time of 1 hour approximately, according to the temperature. (20°C in this case, if you apply with highest temps the open time is reduced)
 - Apply the product with a short- threaded paint brush or rubber spatula.
- Apply immediately.

The support should be covered with EPOAIS 10. In case of joining old hardened concrete to new concrete, apply to the latter within the open time of the mix.

The expected physical and chemical resistances are achieved after 7 days.

Clean up

With our DISOLVENTE EPOXI before the product hardens. Once hardened, it can only be removed by mechanical means.

Data sheet

Colour/sGrey

Open timeaprox. 1 hour at 20°C

DensityComp. A: 1,45 Kg./Lt.± 0,05 a 20° C

DensityComp. B: 1,02 Kg./Lt.± 0,05 a 20° C

ViscosityComp. A: 20.000 + - 4.000 mPas

Drying time12 hours at 20°C

Mix proportion53 A/47 B

AdherenceAdhesion to concrete> 1,5 N / mm², broken concrete

Compressive resistance> 60 N/mm²

Flexural strength resistance> 30 N/mm²

Temperature of workbetween + 10 y + 30°C

Performance

2 m² per kg in concrete union

Storage



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teis.es

síguenos en:



2 years, in their original packagings, properly closed, without exposing to extreme temperatures, protected from the weather, in a dry and airy place.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:

