



## Description

Aerating additive for making mortars more workable. PLAIS added to the mixing water provides a wide plasticity to mortar and concrete, increasing its manageability by allowing reduced water mixing.

Dosages:

Normal: 1 l. / 2500 kg of cement.

Super: is diluted with water in 1:3 ratio, using 20 cc of dilution per sack of cement. 1 l / 10,000 kg of cement.

## Aplication

Plais N is used when it's necessary to improve the workability of mortar and concrete, to slightly reduce the water/cement ratio, to achieve a better finish of the molded parts, to increase mechanical strength. Cohesion increases avoiding segregation, increases the hardened mortar's resistance to frost. Does not change the setting and hardening times.

## Surface preparation

Not applicable.

## Modes of application

Mix the package contents for the correct homogenization of the product.  
-Plais N is added to the mixing water in the ratio of 1L per 2,500 kg. Of cement.  
It is recommended to add 10 cm<sup>3</sup> of PLAIS N to mixing water for every 25 kg

of cement.

- It thus enables to reduce the A/C ratio so as to obtain an improved finish for moulded pieces by increasing their mechanical resistance.

## Clean up

With plentiful clean water

## Data sheet

Colour/dark brown

Density 1,03 Kg/L. (+-) 0,05 g/cm<sup>3</sup>.

PH 7 ± 1

Solid content > 25%

## Performance

According to use

## Storage

During 3 years in their original packagings, properly closed in a dry and cool area, and at temperatures above 4 ° C.

## Security

## Supplementary information:

EUH208: EUH208: Contains 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: desarrollo@teais.es

síguenos en:



EUH210: EUH210:Safety data sheet available on request.



 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
 Telf.: 981 602 111  
 Fax.: 981 601 508  
 Email.: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

