



Descrição

Aplication

It is mostly used in works which require to place concrete under water such as maritime works, dock building, drain pipes, etc It is recommended for concrete that needs increased durability in an aggressive surrounding. It also improves the carbon dioxide diffusion.

Surface preparation

Not applicable.

Modes of application

- HUMOSIL should be dry mixed with the complementary concrete components.
- Its dose can range between 2 to 10% of cement weight.
 - Mix with water thoroughly until the appropriate mix is obtained.

Clean up

Tools must be cleaned with large amounts of water.

Data sheet

Powder density 0,575 g/mL.

Chlorine content < 0,1%

Thin layer 90 % inferior to 1µm.

-SiO₂ > 90%.

Performance

30 kg/m³ of concrete

Storage

It is recommended to store this product for 1 year in its tightly closed original packages.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:

