



Description

Micro-concrete without retraction, very fluid, with particle-size below 2 centimetres that offers high mechanical resistances when it becomes harden. Useful as a final coat for the machine fitting, in reinforcement of structures and pavements, filling of imperfections, etc. It must be amassed with water. Grey cement colour.

Application

It is used for filling by pouring under support plates, filling of machine supports, bridge bearings and cranes, anchoring of metallic elements such as metallic supports, bolts, poles. Anchorings of concrete poles, pillars on prefabricated construction, filling of cracks, cavities, etc. The application thickness must be from 10 to 30 cm.

Surface preparation

The surface must be cleaned, free of greases, oils, dust, etc, compact, uniform and slightly dampened. The metallic elements must be free of oxide. The cleaning of the surface must be done by mechanical means.

Modes of application

HORMIFLUIS must be mixed with water in the proportion of 3,5 litres per 25 kg sack.

- The mixture must be done manually or with low revolution electric mixer (300-500 rpm).
- HORMIFLUIS is placed by pouring immediately after of the mixing in order to benefit its self-leveling

properties and soft expansive effect as well.

-The support must be dampened (no waterlogged) in order to improve the adherence in the cases which Epoxi bonding bridge is not used.

-The fillings under plates must have a hole that allows eliminate the inside air.

Avoid applying the product when it is freeze, low temperatures, snow, etc.

-In all cases of application is very important that the filling curing must be done based on HORMIFLUIS. To this end is suitable to irrigate the surface once the material hardens and keep it wet at least 72 hours.

-It should be considered that the material requires a mold to lodge in.

Clean up

With plenty of water.

Data sheet

Powder density $1,350 \pm 0,050$ g/cc.

Mass of density $2,100 \pm 0,050$ g/cc.

Curing density $1,950 \pm 0,050$ g/cc.

Water absorption $14 \pm 1\%$

Capillarity < 1,5% at 60 minutes

Water retention > 97%

Adherence > 1 N/mm²

Compressive resistance > 650 kg/cm²

Flexural strength resistance > 80 kg/cm²

Colour/sgrey cement

Temperature of work from 5 to 30 °C

zzzzzz

zzzzzz

zzzzzz

zzzzzz

zzzzzz

zzzzzz



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

Telf.: 981 602 111

Fax.: 981 601 508

Email.: desarrollo@teais.es

síguenos en:



Performance

20kg/sqm per 1cm of thickness

Storage

2 years in their original packages, tightly closed, avoiding the exposition to extrem temperatures, keeping it away from the weather and in cool and open-air places.



📍 Avda. da Enerxía, nº 153, PoL Ind. de Sabón
15143 Arteixo, A Coruña
📞 Telf.: 981 602 111
📠 Fax.: 981 601 508
✉️ Email.: desarrollo@teais.es

síguenos en: