

MORIS RAPIDO, Quick Thixotropic mortar of hardening setting



Descrição

Thixotropic mortar without retraction specially designed for repairing. Suitable for the restauration of damaged surfaces by iron oxide spreading. It protect the metallic armours combined with TEAIS PROTECOR and working properly with concrete in the face side. It has a big resistance from the compression. Colour: cement grey.

Aplication

For repairs requiring swiftness, in filling voids, in pavement repair, on bolt anchors, especially in ventilated facades.

Surface preparation

Must be clean, without grease, no dust or loose parts, compact and conveniently wet.

Modes of application

Clean up

With a lot of clean water.





Data sheet

Powder density

Mass of density

Curing density

Water absorption

Capillarity

Water retention

Colour/s

Compressive resistance

Flexural strength resistance

Performance

2 kg per sqm in 1 mm layer

Storage

Two years, in their original bags, tightly closed, without exposing to extreme temperatures, protected from the weather and in dry and ventilated.

Security





Indications of danger:

H315: H315: Causes skin irritation.

H317: H317: May cause an allergic skin reaction.

H318: H318: Causes serious eye damage.





Email.: desarrollo@teais.es

Prudence advice:

P271: P271Use only outdoors or in a well-ventilated area.

P280: P280:Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352: P302+P352:IF ON SKIN: Wash with plenty of soap and water.

P304+P340: P304+P340:IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.

P305+P351+P338: P305+P351+P338:IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310: P310: Immediately call a POISON CENTER or doctor/physician.

P403+P233: P403+P233: Store in a well-ventilated place. Keep container tightly closed.

P501: P501:Dispose of contents/container in accordance with local/regional/national/international regulation



