CAPILAIS N, MORTAR FOR CAPILLARITY MOISTURE SANITATION



Description

Special mortar for the cleaned of the facade or wall afected by rising capillary damp. Before applying the CAPILAISN mortar TEAIS CAPI C must be injected in order to reduce as possible the capillary on the fancings. Indoors are cladding with PERLAIS M or PERLAIS E and outdoors with REPOIS M o REPOIS R. White colour.

Aplication

It is used for cleaning walls and facades affected by rising dampness.

Surface preparation

The background of application must be free of grease, oil, dust or paint. Any previous covering, if any, must be removed until the support is compact and stable. Dampen the support before the application of CAPILAIS.

.

Modes of application

Mix with 25% of water approximately (25 litres of water for every 100 kg of

Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es

síguenos en:

product). Leave to stand for 5 to 10 minutes. Then apply in a thickness of 10 to 15 mm and never smoothen with a trowel. Finally leave to dry for 1 to 7 days depending on room temperature.
- In interiors, PERLAIS-E are used. In exteriors, PINSIL D.
If humidities capillarity prior application of a system of injections to cut rising damp, as the Teais Capi C system that allows efficient lock moisture wicking, and then if you will need can end the Capilais mortar.

Clean up

Clean using large amounts of water.

Data sheet

Powder Density1,15 ± 0,05 g/cc

Water Absorption20 ± 3%

Bulk Density1,950 ± 0,05 g/cc

Adhesion> 2 Kg/cm2

Compressive Strength> 30 Kg/cm2

Flexural Strength> 10 Kg/cm2

Color(s)white

Working temperature5 to 30ºC

Performance

20 kg per sqm in 2 mm thick layer.

Storage

It is recommended to store this product for 2 years in its tightly closed original packages, kept away from humidity.

TEAIS
Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es
síguenos en: