



Description

Fluid mortar for using on regularisation layer in floors. MORFLUIS is used as well as a levelling layer with a thickness between 10-30 mm on concrete floors that require levelling. MORFLUIS is a fluid mortar without retraction. Grey colour.

Aplication

MORFLUIS is fluid mortar without retraction, special for screeds on concrete floorings of 10 mm until 30 mm of thickness.

Surface preparation

The surface where MORFLUIS is apply on must be clean, firm, free of dust. If the surface is made of absorbent materials it must be slightly moistened.

Modes of application

Mix with water until obtain a paste with a fluid consistency.

- The mixture can be done manually or with a low-revolution electric mixer (300-500 rpm).
- Spread it on the support slightly wet with a toothed trowel with a thickness between 10 and 30mm.
- While the material is wet a spiked roller can be used in order to remove the entrained air.

Clean up

With plenty of water while the material is wet.

Data sheet

Water absorption 16% aprox

Powder density 1,10 grs/cc

Mass of density 2,05 grs/cc

Curing density 1,70 grs/cc

Adherence > 3 kg/cm²

Compressive resistance > 200 kg/cm²

Temperature of work From 5 to 30°C

Mix proportion

Performance

1,8 kg/sqm per each mm of thickness.

Storage

2 years in their original packages, protected from the weather and stored in cool and dry places.



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email: desarrollo@teais.es

síguenos en:

