



TEAIS RECRCIDOS R35, SPECIAL CEMENT FOR SCREEDS



Descripción

TEAIS RECRCIDOS R35 is a fast cement for the realisation of screeds and filling. It allows a fast put into service. It has high initial resistances. The product must be mixed with ARCUAIS in the next proportions: 1:4 or 1:5 .

Aplication

For making concrete floors or fillings that requires a quick put into service.

Surface preparation

It is no necessary.

Modes of application

Proportion of admixture:

25 kgs of TEAIS RECRCIDOS R35 (1sack).

From 100 to 125 kg of ARCUAIS 0,8,

From 6 to 11 litres of water.

The concrete floor can be stepped on and cladding after 24 hours, if all the recommedations are followed carefully.(20°C and 65 RH).



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

☎ Telf.: 981 602 111

📠 Fax.: 981 601 508

✉ Email: desarrollo@teais.es

síguenos en:



Don't use additives in the admixture.

Clean up

The tools must be cleaned with plenty of water while the material is wet.

Data sheet

Density 1,65 kg/lt

Compressive resistance From 35 a 45 N/mm² according admixture.

Performance

According with blends.

Storage

Two years in their original packages stored in cool and dry places.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email.: desarrollo@teais.es

síguenos en:

