



Descripción

Liquid for cleaning and turning the slate rust in protective. Passiveness agent in black colour.

Aplication

In slate cladding with rusted metallic pyrites due the weathering.

Surface preparation

The surface must be free of grease and oil stains.

Modes of application

It is applied by brush as a paint or by sprayer and sprayer gun.

- Apply abundantly with the aim that LIPA penetrates in the rust layer and then brush briskly.
- Repeat the operation as many times as necessary.
- Rinse with clean water to remove the rests of dirtiness.
- Let it dry and apply REPAIS or REPAIS ANTIVERDÍN on it as protective and waterproofing.
- Its formulation turns rust in a barrier of black colour resistant to rusting.

- Avoid the contact with glazed surfaces because will become toneless.

Clean up

With plenty of clear water.

Data sheet

Density 1,23 Kg./Lt. +- 0,05 at 20°C.

Colour/sbrownish.

Performance

According to use.

Storage

3 years in their original packages, tightly closed, stored in cools and dry places.

Security



Indications of danger:

H319: Causes serious eye irritation.

Prudence advice:

P264: Wash ? thoroughly after handling.

P280: Wear protective gloves/protective clothing/eye protection/face protection.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:



P305+P351+P338: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P337+P313: If eye irritation persists: Get medical advice/attention.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:

