



Descripción

Waterproofing and asphaltic black paint for retaninig walls systems, gutters in air-chambers. It is also used for the formation of antivapour barriers and primer for placing asphalt cloths too. Two crossed coats must be applied with brush or roll. High throwing and coverage power. Cloudy matt appearance.

Aplication

It is ideal for waterproofing terraces, contention walls, cracks, dams, party walls, etc. Used for priming in supports that are protected with Aluminium or asphalt sheets to improve adherence. In the case of asphaltic sheets the paint must be applied in whole surface for the adhered systems and is applied only in the singular points on floating systems. For protecting and covering metallic reinforced structures so as to prevent corrosion and to avoid contact of wood with earth, etc.

Surface preparation

The surface must be clean, free of greases, oil, loose particles, fungus and mould.

Modes of application

Homogenize well the contents of the packaging
Apply using a paint brush or roller.

- WATERPROOFING: Apply two coating in a crosswise manner, leaving 10 hours in between each coating. In case of structures that are going to be buried a minimum consumption of at least 1 kg/m² should be consider.
- PRIMING: Apply one single coating and leave to dry 10 hours (after this time interval, the sheets are placed followed by pouring the aggregates, water, etc).
- Do not apply if rain is expected or the temperature is lower than 0°C
- LASTOIS IN is not compatible with PVC material.

Clean up

Tools must be cleaned using TEAIS greasy solvent DISOLUAIS.

Data sheet

Density 0,97 Kg./Lt. +- 0,01

Aspect Mate.

Solid content > 55%

Colour/s Dark brown

Dry upon touching 1 hour at 20 ° C for layers of 0.150 kg / m²

Dry for repainting 12 hours at 20 ° C for layers of 0.150 kg / m²

Temperature of work 5 to 30°C

Performance

2 sqm per liter

Storage

1 year in their original packages and tightly closed. Protected from the weather and in cool and dry places..

Security



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teis.es

síguenos en:



Indications of danger:

H226: Flammable liquid and vapour.

H335: May cause respiratory irritation.

H336: May cause drowsiness or dizziness.

H411: Toxic to aquatic life with long lasting effects.

Prudence advice:

P210: Keep away from heat/sparks/open flames/hot surfaces. ? No smoking.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P303+P361+P353: IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin with water/shower.

P304+P340: IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.

P370+P378: In case of fire: Use ? for extinction.

P403+P233: Store in a well-ventilated place. Keep container tightly closed.

P403+P235: Store in a well-ventilated place. Keep cool.

P501: Dispose of contents/container in accordance with local/regional/national/international regulation

