



Descripción

Continuous monolayer coating, consisting of a mortar based on that, fresh aggregate is projected between 5 and 8 mm. Ideal for facade cladding, both concrete and brick. Colors: According to the card. Factory price.

Aplication

As coating masonry facades. To bring uniformity to a new work on concrete, concrete blocks, bricks, etc. Rehabilitation of tiling, replacing paint or plastic coatings.

Surface preparation

Must be clean, resistant, without greases, oils, flat, without holes or significant protrusions and slightly moistened.

Modes of application

It has to be mixed with a $26 \pm 3\%$ of water on weight, in concrete mixer, manually or by low-revolution electric mixer. The time of amassed must be from 5 to 8 minutes.

-Let rest from 3 to 5 minutes.

Mixture's pot life: from 45 to 60 minutes.

Fresh mortar must be applied with a trowel or with a application machine. The minimum thickness must be 10 mm minimum with a 15mm average.

When the layer is still fresh the jonquils must be placed doing the cutting at length(maximum recommendable distance between joints is of 7 meters the verticals and 2,5 horizontals). Subsequently the agreggate or stone must be applied using a trowel in order to obtain the smoothing of the mortar and the agreggate.

-Don't apply with rain forecast, frost, high winds or bad weather.

-The joints between different nature supports and singular points must be built with resistance to alkalis fiberglass TEJIAIS 10.

-The covering is no suitable for exposed and inclined horizontal surfaces.

-The top edges must be protected against rain penetration.

-It is no necessary to apply it on the concrete, plaster, paints, metal surfaces, plastic or low mechanical resistance.

Clean up

With plentiful clean water while the material is fresh, once hardened can only be removed by mechanical means.

Data sheet

Water absorption $26 \pm 2\%$

Powder density $1,250 \pm 0,05$ g/cc.

Mass of density $1,750 \pm 0,05$ g/cc.

Curing density $1,650 \pm 0,05$ g/cc.

Water retention $> 90\%$

Capillarity $< 0,15$ (kg/m² min 1/2)

Adherence $> 0,3$ N/mm²

Compressive resistance > 9 N/mm²

Flexural strength resistance $> 3,5$ N/mm²

Euroclasses A1


Temperature of work 5 to 30°C

Performance



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email: desarrollo@teis.es

síguenos en:



Paste: 18 kg per sqm. Gravel: 10 to 12 kg by smq

Storage

1 year, in their original packagings, properly closed, protected from weather and stored in a cool and very dry place.

Security



Indications of danger:

H315: Causes skin irritation.

H317: May cause an allergic skin reaction.

H318: Causes serious eye damage.

H335: May cause respiratory irritation.

Prudence advice:

P271: Use only outdoors or in a well-ventilated area.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352: IF ON SKIN: Wash with plenty of soap and water.

P304+P340: IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.

P305+P351+P338: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310: Immediately call a POISON CENTER or doctor/physician.

P403+P233: Store in a well-ventilated place. Keep container tightly closed.

P501: Dispose of contents/container in accordance with local/regional/national/international regulation