



# REPOIS R, ONE COAT MORTAR WITH SCRATCHED FINISH



# Descrição

One coat mortar with scraped finish. It is applied with a trowel onto the support to be rendered. After a period of 8 to 24 hours, depending on room temperature, scraping is carried out using a special trowel.

# Aplication

It is used for rendering facades made of blockwork or brickwork. It also gives uniformity to new jobs performed on concrete, brickwork, etc. It is also used for restoring purposes so as to replace paints and plastic renders.

## Surface preparation

The background of application must be clean, resistant, free of grease, oil, uniform, free of any ridges or irregularities, by being slightly damp.

## Modes of application

Mix with water in a proportion of  $19 \pm 3\%$  of water in weight, manually or mechanically (concrete mix, slow mixer, etc).

Apply the fresh mortar mix onto the support to be rendered using a trowel and then smoothen with a ruler.



9 Ayda da Energía, nº 153, Pol. Ind. de Sabón

15143 Arteixo A Coruña

€ Telf: 981 602 111

 Fax.: 981 601 508

 Email: desarrollo@teajs.es

síguenos en:



Proceed to limit the piers by placing the joints in the desired pattern: 7 m vertically and 2.5 m horizontally). Leave to dry partially. After 24 hours(depending on weather conditions), use a special trowel so as to achieve a scraped finish.

It is recommended to apply at least 10 mm thick coating and reaching an average thickness of 15 mm.

## Clean up

Clean using large amounts of water.

## Data sheet

Water absorption  $19 \pm 3\%$

Powder density  $1.350 \pm 0.05$  g/cc.

Mass of density  $1.750 \pm 0.05$  g/cc.

Curing density  $1.800 \pm 0.05$  g/cc.

Capillarity < 0.50% in 60 minutes

Water retention > 97%

Adherence > 2.5 kg/cm<sup>2</sup>

Compressive resistance > 80 kg/cm<sup>2</sup>

Resistance to longitudinal tear > 35 kg/cm<sup>2</sup>

Colour/sgris, blanco, crema, castilla, ocre, rosa, etc. (various colours according to colour chart).

## Performance

20kg and 22kg per m<sup>2</sup> for white colour.

## Storage

It is recommended to store this product for 1 year in tightly closed original packages.

## Security



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

Telf.: 981 602 111

Fax.: 981 601 508

Email.: desarrollo@teais.es

síguenos en:



## Indications of danger:

H315: Causes skin irritation.

H317: May cause an allergic skin reaction.

H318: Causes serious eye damage.

## Prudence advice:

P261: Avoid breathing dust/fume/gas/mist/vapours/spray.

P264: Wash thoroughly after handling.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352: IF ON SKIN: Wash with plenty of soap and water.

P305+P351+P338: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310: Immediately call a POISON CENTER or doctor/physician.

P333+P313: If skin irritation or rash occurs: Get medical advice/attention.

P501: Dispose of contents/container in accordance with local/regional/national/international regulation