

SELLADOR ADOBE, SEALANT AND HARDENER FOR ADOBE SURFACES.



Descripción

Dilution of sythetic resins that applied on adobes, seal and harden its surface allowing transpiration. Apply by brush or roller on the surface to seal.

Aplication

As a sealant and hardener on the surfaces of adobe, in older constructions that requires a superficial consolidation to avoid the formation of dust and increase the durability.

Surface preparation

The surface must be clean, free of greases and dry. Also free of elements that avoid the absorption.

Modes of application

Stir strong the product before the application.

- The supports must be dry, free of elements that avoids the absorption. It can be applied as a previous treatment with lime-based mortars such as REVOGACAL.

Apply by brush or roller without dilute it on the surface to seal at list two layers.

- For the application of the second layer the first one must be completely dry for which from 8 to 12 hours



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
 15143 Arteixo, A Coruña
 Telf.: 981 602 111
 Fax.: 981 601 508
 Email.: desarrollo@teais.es



must spend according with the temperature and relative humidity of environment.

- The application of the sealer not decreases the adherence of any type of rendering wanted to apply subsequently and because improves the surperficial resistance and the anchoring with any rendering working as a fastener at the same time.

- Not apply when a rain forecast, strong wind, freeze or any adverse weather condition is expected.

Clean up

with plenty of clean water while the material is wet.

Data sheet

Density1,05 Kg/L. (+-) 0,05 at 20°C Viscosity12,5 ± 2,5 sec. At 20°C. Layer Ford: 4 mm. Dry upon touching< 30 minutes to touch at 20°C, 65% Relative Humidity Aspecttranslucent liquid Temperature of workfrom 5 to 30°C

Performance

5 sqm per litre in two layers.

Storage

Store in dry and cool place for 2 years maximum. Protect from the weather and extrem temperatures.

Security



Indications of danger:



- Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
 15143 Arteixo, A Coruña
 Telf.: 981 602 111
- Fax.: 981 601 508
- Email.: desarrollo@teais.es



Prudence advice:

P261: Avoid breathing dust/fume/gas/mist/vapours/spray.

P272: Contaminated work clothing should not be allowed out of the workplace.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352: IF ON SKIN: Wash with plenty of soap and water.

P333+P313: If skin irritation or rash occurs: Get medical advice/attention.

P501: Dispose of contents/container in accordance with local/regional/national/international regulation



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

- Telf.: 981 602 111
 Fax.: 981 601 508
- ✓ Email.: desarrollo@teais.es

