



IMPRIMACION INTUMESZAIS, ANTICORROSIVE PRIMER FOR "INTUMESZAIS" PAINT.



Descripción

Antirust primer to use previously to paint with INTUMESZAIS. Solvent : DISOLUAIS.

Aplication

Over metallic elements such as anticorrosive primer for the subsequent application of TEAIS intumescent covering INTUMESZAIS.

Surface preparation

The surface must be tightly closed, free of greases, oils, dust and other polluting agents that decreases the proper adherence on the support. Suitable to jet until SA 2 1/2 grade.

Modes of application

Stir well the content of the package before using.

Apply one coat with a recommended thickness of 35-40 microns preferably with spray gun or Airless.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:



Let it dry 24 hours and then apply INTUMESZAIS.

- Metallic surfaces must be completely free of greases and rust. For that is recommendable the use of mechanical means such as sanding by sanding machine or particle jetting.
- Is very important that the application of the primer is done just after the cleaning of metal to avoid new corrosive process and also once the primer is dry the intumescent paint must be applied.

Clean up

With our solvent DISOLUAIS while the product is fresh

Data sheet

Density 1,5 Kg./Litre \pm 0,05

Solid content in volume 54.4% \pm 1%

Colour/sred

Dry upon touching 10 minutes at 20°C/65% RH

Dry for repainting 24 Hours at 20°C / 65 RH.

Temperature of work From 8 to 30°C

Performance

12 sqm per litre at 35 microns

Storage

2 years in their original packages tightly closed, protected from the weather and stored in a cool and dry place.

Security



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teis.es

síguenos en:



Indications of danger:

H226: Flammable liquid and vapour.

H304: May be fatal if swallowed and enters airways.

H317: May cause an allergic skin reaction.

H332: Harmful if inhaled.

H340: May cause genetic defects .

H350: May cause cancer .

H372: Causes damage to organs through prolonged or repeated exposure .

H400: Very toxic to aquatic life.

H410: Very toxic to aquatic life with long lasting effects.

Prudence advice:

P210: Keep away from heat/sparks/open flames/hot surfaces. ? No smoking.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352: IF ON SKIN: Wash with plenty of soap and water.

P303+P361+P353: IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin with water/shower.

P304+P340: IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.

P308+P313: IF exposed or concerned: Get medical advice/attention.

P370+P378: In case of fire: Use ? for extinction.

P501: Dispose of contents/container in accordance with local/regional/national/international regulation

Supplementary information:

EUH066: Repeated exposure may cause skin dryness or cracking.

EUH208: Contains . May produce an allergic reaction.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
☎ Telf.: 981 602 111
📠 Fax.: 981 601 508
✉ Email: desarrollo@teais.es

síguenos en:

