BREPOIS, TWO- COMPONENT EPOXI TAR



Description

Anticorrosive cladding based on coal tar and epoxi resins that acts as barrier in antioxidant systems. Two-component product that must be mixed in proportion of 10A:1B of its weight. The useful life of admixture is 1 hour according the ambient temperature. Ideal for cover an protect surfaces made of iron, steel or concrete against moisture. Black colour.

Aplication

Ideal to cover and protect surfaces made of iron, steel or concrete against the moisture both weathering and buried.

Surface preparation

The iron or steel surface must be completely free of rust, grease or any pollution and treated by a quite good antioxidant such as MINOAIS SUPER. The cementitious supports must be cured (concretes and mortars 28 days minimum).

Modes of application

Homogenize separately each component.
- The admixture must be done with 10 parts of A component and 1 of B component on weight taking into account that the useful life of the admixture is 1 hour (20ºC and 65% RH).

The repainting must be done in intervales of 24 hours until achieve the suitable coat thickness.
- In case of applycation on metals they must be clean and free of greases. If they are ferrous metals is suitable

Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es

síguenos en:

to prime previously with an anticorrosive primer.
- The supports must be completely cured (28 days) in case of application on concrete or mortars supports

Clean up

The tools must be cleaned with DISOLVENTE EPOXI.

Data sheet

DensityAdmixture:1,27 +/- 0,05 Kg./dm3

Volume Solids63 (Brepois) / 67 (Brepois thick coat) ± 1%

Touch Dry30 minutes at 20ºC and 65% de R.H..

Recoatable24 hours

Color(s)black

Working temperatureFrom 8ºC to 25ºC

Performance

5 sqm per kg thickness of 100 microns.

Storage

In their original packages, tightly closed in dry place, wet and temperatures over 5ºC during 2 years.