EPO FOS, SHOP PRIMER EPOXY RESINS.



Descripción

Two-component SHOP PRIMER based on epoxi resins and pigments potencially anti-rust. Reddish colour. Useful life. 6 hours.

Aplication

Its function is the protection of the newly steel sand- blasted

Surface preparation

The suitablest way is the sand-blasted for new construction or reparation.

Modes of application

Homogenize separately the components before mixing.
- Mix manually or mechanically by a low-revolution electric mixer (3000-5000rpm).
-The suitable application is by AIRLESS. It is not recommendable the use of solvent. If it is necessary only use a 3% maximum of EPOXI SOLVENT.

In special cases, mainly for retouching, also can be use a brush, roller or usual application-gun, using EPOXY SOLVENT.

Clean up

TEAIS
Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es
síguenos en:

With TEAIS EPOXY SOLVENT

Data sheet

AppearanceGlossy

Color(s)Reddish

Volume Solids31% admixture

Mix ratio74,44 parts in weight: Component A
25,46 pars on weight: Component B

DensityComp. A: 1,32 (+/-) 0,05 kg/L.
Comp. B: 0,9 (+/-) 0,05 kg/L.Admixture: 1,18 Kg/L (+-) 0,05

Open Time6 hours.

Flash Point25ºC (TAG closed)

Touch Dry10 minutes to touch at 20ºC, 65% Relative Humidity

Dry Hard2 hours hard at 20ºC, 65% Relative Humidity

Service temperatureUntil 150ºC

Working temperatureFrom 8 to 25ºC

Performance

6-8 sqm per litre

Storage

Store in a dry and cool place for 2 years maximum, protected from the weather in their original packages.

TEAIS
Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es
síguenos en: