AC SILVER CR, ANTICORROSION PRIMER



Description

Caoutchou-based antirust primer

Aplication

On ship hulls or elements which are in contact with marine waters.

Surface preparation

Blast grade SA 2 1/2. Otherwise the surface must be free of rust, grease, dust or other pollution.

Modes of application

Homogenize well the containt of the package.
- A proper treatment of surface preparation must be done. The surface has to be free of rust in the moment of application. To achieve this, jets particles treatments are suitable.
It must be applied by brush, spray gun or airless.
- Don´t apply it will be rain, strong winds, freezes or with bad weather.

Clean up

Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es

síguenos en:

With DISOLUAIS solvent.

Data sheet

Color(s)light reddish and dark reddish

Density1,27 Kg/L (+-) 0,05

Touch Dry30 m at 20º at 65% RH

Recoatable6 h ay 20º at 65% RH

Dry Hard3 h at 20º at 65% RH

Appearancesemi-matt

Volume Solids40 %

Working temperaturefrom 8 to 30ºC

Performance

From 4 to 5 sqm per litre

Storage

Store it in dry and cool places for 2 years maximum in its original package,tightly closed and protected from the weather.

TEAIS
Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es
síguenos en: