



AC SILVER CR, ANTICORROSION PRIMER



Description

Caoutchou-based antirust primer

Application

On ship hulls or elements which are in contact with marine waters.

Surface preparation

Blast grade SA 2 1/2. Otherwise the surface must be free of rust, grease, dust or other pollution.

Modes of application

Homogenize well the content of the package.

- A proper treatment of surface preparation must be done. The surface has to be free of rust in the moment of application. To achieve this, jets particles treatments are suitable.

It must be applied by brush, spray gun or airless.

- Don't apply it will be rain, strong winds, freezes or with bad weather.

Clean up



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email: desarrollo@teais.es

síguenos en:

With DISOLUAIS solvent.

Data sheet

Colour/slight reddish and dark reddish

Density 1,27 Kg/L (+-) 0,05

Dry upon touching 30 m at 20º at 65% RH

Dry for repainting 6 h ay 20º at 65% RH

Hard dry 3 h at 20º at 65% RH

Aspect semi-matt

Solid content in volume 40 %

Temperature of work from 8 to 30°C

Performance

From 4 to 5 sqm per litre

Storage

Store it in dry and cool places for 2 years maximum in its original package, tightly closed and protected from the weather.



Avda. da Enerxía, nº 153, PoL Ind. de Sabón

15143 Arteixo, A Coruña

Telf.: 981 602 111

Fax.: 981 601 508

Email.: desarrollo@teais.es

síguenos en:

