AUTOEMPLAIS, PLASTER FOR METALLIC ELEMENTS





Description

Putty for metallic elements formed by two-components, that has a high filling capacity, fast dry and easy-sanding once dries. Is suitable for filling dents and cracks on metallic elements.

Aplication

As a filling for metallic elements.

Surface preparation

The surface must be clean, free of dust, greases, oils and others polluting agents, sanded and completely dry.

Modes of application

Mix in proportion of 1% of catalyst over the putty. The content of the tube is the according quantity of metallic package.

The admixture is done in small quantities in the proportion of one tablespoon by the corresponding catalyst.

- The admixture is done manually achieving a good homogenization.

Remove the putty from the package by adifferent spatula than the one to use to do the admixture. Any catalyst portion in contact with the putty in the package would harden it.

Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es

síguenos en:

It dries to touch after 5 minutes and can be hard and sandable after 30 minutes (20ºC and 65% RH).

Clean up

When it is still wet with DINITRAIS TEAIS solvent.

Data sheet

Density1,50 Kg./Lt. ± 0,05.

Color(s)Light beige

Open Time< 5 minutes

Mix ratio100 A by 1B

CompositionResins of polyester, special charges and additives.

AppearanceThixotropic paste.

Performance

According use

Storage

1 year in their original packages and tightly closed, protected form the weather and stored in cool and dry place.

TEAIS
Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es
síguenos en: