LASTOIS POL, ELASTOMERIC POLYURETHANE PUTTY



Description

Putty-elastomeric polyurethane glue, rapid polymerization, for joints flexible and watertight in any form. Colors: White, Gray, Black and Brown. Prices according to order volume.

Aplication

For fixing roof tiles, undulated asbestos cement decks, wood baseboards and skirting boards, sinks, metallic kitchens, etc. Flexible unions on decks, carpentry, installations, etc. Repairing pipes, ducts, etc. For bonding screens, partition walls, synthetic panels, etc. For bonding elements submitted to great efforts, impacts, PVC plates, etc.

Surface preparation

Must be clean, degreased and dry without presence of bitumen or similar.

Modes of application

Apply with a manual or pneumatic gun(by avoiding any air occlusion) by keeping the nozzle at an appropriate distance.

Generally, no priming is required. In case it is necessary, IMPRIMAIS SUPER or IMES will be used(on cement,

Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es

síguenos en:

concrete or wood).
It is applied in cords such as when filling cracks or joints and then smoothened by pressing with a putty knife
During the first interval of time(before reticulation), use hydraulic jacks, pillars, wedges, etc, so as to ensure proper bonding of the elements..
- Elastomer of high modulus of elasticity (polyurethane): B1.
Resistant to salt water, fresh water, detergents, dilute acid, dilute alkali and hydrocarbons (temporarily).
No corrosive and has high adhesion and sealing.
-Width Maximum board is 35 mm, the recommended widths are between 10 and 25 mm, joints less than 5 mm must be opened to be sealed.
-For Elastic sealed the ratio of the joint width and depth is 2: 1, for which in general it should be placed together with a cellular polyurethane cord used for filling (Jupo), which will determine the form factor .
- Maximum deformation: 15%

Clean up

With our DISOLUAIS

Data sheet

Density1,26 Kg./Lt. +- 0,05

Shore A hardness40 +- 5

CompositionMonocomponent elastomer polyurethane

Elongation at Break> 600% (DIN 53504).

Color(s)White, grey, black and brown

Service temperature-30ºC to +90ºC.

Working temperature5ºC to 35ºC

Performance

12 m on 5x5 mm joint

Storage

12 months, in their original packagings and properly closed. In stable environments temperatures between +10 to +25 ° C and protected from the weather.