



## Descripción

Powder product which amassed with water becomes and a suitable product for sealing joints of tiles, stone slabs, glass slabs, etc. It's a very good option for decorative sealing of open and close joints of stone slabs, terraces, tiles, etc. THIN TYPE is used for joints until 5mm thickness while THICK TYPE is used for thickness of more than 5 mm. The prices depending on the colours and quantities.

## Aplication

Rejuntais is used for sealing joints on floor and wall coverings, in indoors or outdoors, in bathrooms, kitchens, swimming pools, pavements in general, for its excellent glossy appearance is very suitable for coatings onto coatings based on porcelain tiles, marble , granite, or any material that requires high functional and esthetic quality groutings .

With additives to prevent mold growth.

## Surface preparation

The joints must be clean and free of material across its length and depth. Ceramics should be protected during application. To apply the grouting, the bonding must have at least 24 hours in walls and 48 floors.

## Modes of application

Mix with water in a clean container until obtaining a pasty mass.

- Mechanical mixture is done with a low-revolution electric mixer: 300-500 rpm.
- Let it stand for 3-5 minutes before applying.
- Apply with the aid of a spatula or a grouting gun (APLIJUN).
- The material must be well compacted into the joints..
- The application must be done perpendicular to the joints pressing the grout and removing the remaining material.
- It is cleaned with a hard and slightly wet sponge after the time-work is more than 20- and less than 30 minutes in order to the material becomes too much hardness.
- The final cleaning once the material has hardened it can be done with our cleaning products COAIS (a test should be done in a small surface to be sure that spots doesn't appear).

- When placing glass windows, mix with AGLUTAIS 50.

- REJUNTAIS F is used for joints of maximum 5 mm wide, and REJUNTAIS G for 5 - 10 mm wide.

REJUNTAIS F is used for joints of 5mm wide maximum and REJUNTAIS G is used for joints thicker than 5mm.

## Clean up

With plentiful clean water while the mortar is fresh. After hardening can only be removed mechanically.

## Data sheet

Water absorption  $30 \pm 3\%$  relativa al agua del amasado

Powder density  $1,00 \text{ g/cc.} \pm 0,05$

Mass of density  $1,950 \text{ g/cc.} \pm 0,05$

Curing density  $1,900 \text{ g/cc.} \pm 0,05$

Water retention  $> 97\%$

Capillarity  $< 0,40\%$  at 60 minutes

Adherence  $> 1 \text{ N/mm}^2$

Compressive resistance  $> 150 \text{ kg/cm}^2$  values at 28 days (EN 12808-3)

Flexural strength resistance  $> 50 \text{ kg/cm}^2$  values at 28 days (EN 12808-3)

Colour/s blue, brown, grey, white, black, etc.

Retraction  $< 3 \text{ mm/ml}$  at 28 days

Water absorption at 30 minutes  $< 5 \text{ gr}$

Compressive resistance  $> 150 \text{ kg/cm}^2$  after freeze-thaw cycles



% Solid content in weight < 1000 mm<sup>3</sup> (EN 12808-2)

Water absorption at 240 minutes < 10 gr

## Performance

F: 0,65 kg/m<sup>2</sup>, and 5 mm; G: 1,3 kg/m<sup>2</sup>, and 10 mm.

## Storage

2 years, in their original packagings, properly closed and protected from the weather, stored in cool and dry place areas.

## Security



### Indications of danger:

H315: H315: Causes skin irritation.

H317: H317: May cause an allergic skin reaction.

H318: H318: Causes serious eye damage.

H335: H335: May cause respiratory irritation.

### Prudence advice:

P271: P271: Use only outdoors or in a well-ventilated area.

P280: P280: Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352: P302+P352: IF ON SKIN: Wash with plenty of soap and water.

P304+P340: P304+P340: IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: desarrollo@teis.es

síguenos en:



P305+P351+P338: P305+P351+P338:IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310: P310:Immediately call a POISON CENTER or doctor/physician.

P403+P233: P403+P233:Store in a well-ventilated place. Keep container tightly closed.

P501: P501:Dispose of contents/container in accordance with local/regional/national/international regulation



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

