



POLIURETANO 80/20, POLYURETHANE BASED PAINT FOR INDOORS AND OUTDOORS



Description

Paint based on aliphatic polyacrylates and isocyanates. With this combination an excellent gloss retention, light resistance and chalk are achieved. It is a two-component system. Consult prices for other colours.

Application

Walls with cementitious surfaces. Metal structures in general. Indoor and outdoor pavers.

Surface preparation

Must be clean, degreased, free of foreign particles and substances, appearing perfectly dry. Advisable light sanding.

Modes of application

Treat the support by using a good antioxidant system such as EPOFOS, EPOCOR, etc. In case of a cement based support, apply the primer IMPRIDUR.

Mix the two components in the proportion of 80 parts of



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo, A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email: desarrollo@teais.es

síguenos en:

component A to 20 parts of component B in weight.

Apply one to two coatings.

Mix the amount that can be applied within 2 to 3 hours. After this open time, the mix can no longer be used.

Apply with a paint brush or airless equipment.

- Dont apply with bad weather conditions

- Min curing of concrete to apply 28 days, dont apply with capillarity moisture problems

Clean up

With our SOLVENT P.U.

Data sheet

Density 1,32 +- 0,05 at 20°C.

Dry for repainting 24 Hours /20°C/65% (with the same product).

Dry upon touching

Open time 3 Hours/20°C/65%

Dry film thickness 60-100 micras.

Aspect glossy

Colour/s white and other by order

Mix proportion 80 parts of A and 20 parts of B in weight

Performance

5 m² /kg.

Storage

1 year, in their original packagings, properly closed, without exposing to extreme temperature, protected from the weather in a dry and airy place.



Avda. da Enerxía, nº 153, Pol. Ind. de Sabón

15143 Arteixo, A Coruña

Telf.: 981 602 111

Fax.: 981 601 508

Email.: desarrollo@teais.es

síguenos en:

