POLIURETANO 80/20, POLYURETHANE BASED PAINT FOR INDOORS AND OUTDOORS



Description

Paint based on aliphatic polyacrylates and isocyanates. With this combination an excellent gloss retention, ligth resistance and chalk are achieved. It is a two-component system.
Consult prices for other colours.

Aplication

Walls with cementitous surfaces. Metal structures in general. Insidoor and outdoor pavers.

Surface preparation

Must be clean, degreased, free of foreign particlesand substances, appearing perfectly dry. Advisable light sanding.

Modes of application

Treat the support by using a good antioxidant system such as EPOFOS, EPOCOR, etc. In case of a cement based support, apply the primer IMPRIDUR.
Mix the two components in the proportion of 80 parts of

Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es

síguenos en:

component A to 20 parts of component B in weight.
Apply one to two coatings.
Mix the amount that can be applied within 2 to 3 hours. After this open time, the mix can no longer be used.
Apply with a paint brush or airless equipment.
- Dont apply with bat weather conditions
- Min curing of concrete to apply 28 days, dont apply with capillarity moisture problems

Clean up

With our SOLVENT P.U.

Data sheet

Density1,32 +- 0,05 at 20ºC.

Recoatable24 Hours /20ºC/65% (with the same product).

Touch Dry

Open Time3 Hours/20ºC/65%

Dry Film Thickness60-100 micras.

Appearanceglossy

Color(s)white and other by order

Mix ratio80 parts of A and 20 parts of B in weight

Performance

5 m2 /kg.

Storage

1 year, in their original packagings, properly closed, without exposing to extreme temperature, proctected from the weather in a dry and airy place.

TEAIS
Avda. da Enerxía, nº 153, Pol. Ind. de Sabón
15143 Arteixo,A Coruña
Telf.: 981 602 111
Fax.: 981 601 508
Email.: desarrollo@teais.es
síguenos en: