



**TEAIS FONPOL A, Two component polyurethane base for joinery and joinery products.**

## Descrição

Colourless two component fast dry primer. Suitable for wood with low porosity and application of open or close pore. Catalytic: F29/N11. Solvent: DISOLAIS.

## Aplication

Ideal for wooden protection both new and restored. Tapaporos is the suitable primer for all types of wood where a high quality decorative finish is required according with the properties and characteristics of the product.

## Surface preparation

Must be quite clean, free of greases, wax, dust, loose particles and perfectly dry and flat.

## Modes of application

Stir the content of the package properly before using.

- Before applying the product the admixture must be done at 50%, it means that for example we must mix 1 litre of A component with 1/2 litre of B component (TEAIS CATALIZADOR F29/ TEAIS CATALIZADOR N11).
- It can be applied with an aerographic gun, air- less, brush, roller, etc?

## Clean up

With TEAIS CLEANING SOLVENT.

## Data sheet

AspectViscous liquid

Colour/sYellowish



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:



Density 0,99 kg/Lt  $\pm$  0,05 a 20 °C

Mix proportion 2/1

Dry for repainting 4 hours

Dry upon touching 1 hour

Viscosity Admixture: 22 s CF n4

## Performance

---

From 8 to 10 sqm/litre

## Storage

---

2 years in their original packages, tightly closed, avoiding extreme temperatures, protected from the weather and in dry and open-air places.



📍 Avda. da Enerxía, nº 153, Pol. Ind. de Sabón  
15143 Arteixo, A Coruña  
☎ Telf.: 981 602 111  
📠 Fax.: 981 601 508  
✉ Email: [desarrollo@teais.es](mailto:desarrollo@teais.es)

síguenos en:

